

Natural product antifoulants

T. V. Raveendran* and V. P. Limna Mol

National Institute of Oceanography (Regional Centre), Council of Scientific and Industrial Research, Kochi 682 018, India

Natural Product Antifoulants (NPAs) have been proposed as one of the best replacement options for the most successful antifouling agent, tri-*n*-butyl tin (TBT), which, due to its ecological incompatibility, is currently facing total global ban imposed by International Maritime Organization (IMO). Realizing the importance, commercial and industrial, of immediately finding a suitable replacement for TBT, the research on NPAs has gathered considerable momentum during the last two decades, as evidenced from the sudden spurt in the number of publications and the number of NPAs being reported. Although commendable effort has been expended, more challenges remain ahead before realizing their applications at an industrial scale.

Keywords: Antifouling, biofouling, natural products, secondary metabolites, TBT.

MARINE biofouling, the attachment and growth of sessile organisms on artificial structures submerged in the sea, incurs substantial financial implications to the marine engineering constructions comprising ships, offshore platforms, jetties and harbours¹⁻⁴. The problem is so severe that worldwide the expenditure incurred on antifouling measures alone is approximately US\$ 6.5 billion a year⁵. Application of antifouling coatings has been a widely employed strategy for controlling fouling on underwater marine structures. Among the various coatings, Self-Polishing Copolymer antifouling paints (SPCs) with tributyl tin (TBT) as biocide was the most preferred⁶. Thus, 70% of the world's shipping fleet was coated with self-polishing TBT paints⁷, accounting for two-thirds of the total antifouling market⁸ in the 1990s. Unfortunately, this most popular antifouling coating, having a life time up to five years, also turned out to be the most toxic⁹. Excessive introduction of this biocide into the environment caused shell thickening in oyster population and imposex in gastropods¹⁰⁻¹³. Further, their build-up in the marine food chain through bioaccumulation and biomagnification attracted utmost concern. The subsequent total global ban imposed on TBT-based coatings by the International Maritime Organization (IMO) led the antifouling paint industry into a very precarious situation¹⁴. Although copper and organic booster biocides blended with copolymers have widely been used as immediate alternatives

for TBT, considering their ecotoxicity, durability and cost factors, most of these biocides might be considered as interim solutions rather than real alternatives for TBT^{15,16}.

TBT-replacement antifouling coatings, therefore, have to be environmentally acceptable and at the same time, should maintain a long life⁶. Natural Product Antifoulants (NPAs) have been proposed as one of the best possible alternatives in this context^{6,15,17,18}. The NPAs are advantageous over conventional toxic biocides in that they are less toxic, effective at low concentrations, biodegradable, have broad spectrum antifouling activity and their effects are reversible¹⁹. Moreover, they have evolved within the system through millions of years of evolution. NPAs, especially those having anaesthetic, repellent or settlement inhibition properties, without being biocidal, are the most desired¹⁵. In general, the search for NPAs is greatly encouraged by the fact that the effect of these compounds is based more on repellent mode of action than on strong toxicity.

The majority of NPAs identified so far are terpenoids, steroids, carotenoids, phenolics, furanones, alkaloids, peptides and lactones. They have been isolated from a wide range of organisms of which the major groups are represented by sponges²⁰⁻²² and soft corals²³⁻²⁵, as they are well known for maintaining foul-free surfaces²⁶. Other groups include seaweeds, seagrasses²⁷⁻²⁹, tunicates^{30,31}, bryozoans^{32,33}, mangroves and microorganisms³⁴⁻³⁶. In recent studies, crustaceans such as lobster and shore crabs, echinoderms such as sea stars and sea urchins, as well as egg cases of molluscs and dogfishes were investigated to elucidate their antifouling strategy³⁷⁻³⁹. Accordingly, over 145 NPAs have thus far been isolated and identified from marine sources (Tables 1-5).

In general, a sudden spurt in the number of publications on NPAs in 1990s and 2000s was evidently a consequence of the anticipated ban on TBT by IMO beginning January 2008 (Figure 1).

Present scenario

The search for bioactive compounds from marine organisms was initiated²⁷ in the 1960s. The possibility of collecting organisms directly from the ocean with the use of SCUBA opened the door to a largely untapped resource with a range of unique structures and novel compounds. The common methodology employed in the isolation of

*For correspondence. (e-mail: tvravi@nio.org)

Table 1. Antifouling activity detected in sponges

Sponge species	A/F compound	Activity	Laboratory	Year
<i>Aaptos</i> sp.	Aaptamine	Z.m.	Univ M, USA	2006
<i>Acanthella acuta</i>	Crude extract	B.n.		1993
<i>Acanthella cavernosa</i>	Bact. extract	B.a.	FBP, Japan	1995
	Kalihipyran B, 15-formamido Kalihinene, kalihinol A, 10 β -formamidokalihinol A, 10-isocyano-4-cadinene, isocyanotheonellin	B.a.	FBP, Japan	1996
	Steroid peroxidase	B.a.	FBP, Japan	1998
	10-formamide-4-cadinene	B.a.	FBP, Japan	2003
	Isocyanide	B.a.	ARL, Japan	2004
	Kalihinol A	H.e.	CML, China	2006
<i>Agelas conifera</i>	<i>Bromopyrroles</i>	B. a.		1991
<i>Agelas mauritiana</i>	Mauritiamine	B.a.	FBP, Japan	1996
	Epi-agelazine C	U.c.	MB I, Japan	1997
<i>Agelas</i> sp.	Agelazine D	B.i.	Uppsala Univ Sweden	2008
<i>Aplysilla glacialis</i>	1-Methyl adenine	Ab		1992
<i>Aplysina fistularis</i>	Aerothionin, Homoaerothionin	H.r.		1985
<i>Axinella</i> sp.	Isonitriles, Isothiocyanates	P.pa.; S.t.; H.r.		1985
<i>Axinyssa</i> sp.	Axinyssimide A, B, C; 2-chloro-10,11-dihydroxy-3-methylene-7,11-dimethyl-6-dodecenyldicholromethylenamine	B.a.	FBP, Japan	1998
<i>Azorica pfeifferae</i>	Crude extract	B.a.	RRL, Orissa	1999
<i>Cacospongiascalaris</i>	Dihydrofurospingin-II	B.a.	NC Univ, UK	2005
<i>Callyspongia</i> sp. 1	Crude extract	Bact.; Dtm.		2005
<i>Callyspongia</i> sp. 2	Crude extract	Bact.; Dtm.		2005
<i>Callyspongia plicifera</i>	Crude extract	B.a.	CML, China	2006
<i>Callyspongia pulvinata</i>	Crude extract	Bact.; Dtm.		2005
<i>Callyspongia truncata</i>	Calytetrayne, Callyspongin B, Callytriol C	B.a.	FBP, Japan	1997
<i>Crambe crambe</i>	Crambescins	B.n.		1997
<i>Craniella</i> sp.	Crude extract	B.n.		1993
	Crude extract	Ab	NIO, Goa	1994
	Crude extract	N.su.; N.c.		1994
<i>Crella incrustans</i>	lyso-PAF	B.n.		1996
<i>Dendrilla herbacea</i>	Herbacin	B.n.	Vizag	1991
<i>Dendrilla nigrae</i>	Crude extract	Af	Biotechnology Dept, Kanyakumari	2004
<i>Dysidea ambliia</i>	Ambliol-A, Pallescensin-A	S.t.; H.r.		1985
<i>Dysidea avara</i>	Avarol	B.a.	Univ Athens, Greece	2007
<i>Dysidea</i> sp.	Crude extract	B.a.	NC Univ, UK	2005
<i>Erylus formosus</i>	Formoside	F.i.; Algae		2000
<i>Geodia barrette</i>	Barettin	B.i.	Uppsala Univ, Sweden	2006
<i>Halichondria</i> sp.	Crude extract	Bact.; Dtm.		2005
<i>Haliclona</i> sp.	Cyclic bis-(3-alkylpiperidine)	H.c.	MBI, Japan	2002
	Haliclonamides	M.e.		
<i>Haliclona</i> sp.	Crude extract	P.vi.	NIO, Goa	1998
<i>Haliclona cymaeformis</i> var. 1	Haliclonamides	Bact.; Dtm.		2005
<i>H. cymaeformis</i> var. 2	Crude extract	Bact.; Dtm.		2005
<i>Haliclona? Cinerea</i>	Undescribed mixture	P.pa.; S.t.; H.r.		1985
<i>Haliclona exigua</i>	bis-1-oxaquinolizidine alkaloids	B.a., F.bact	NIO, Kochi	2009

(Contd)

REVIEW ARTICLE

Table 1. (Contd)

Sponge species	A/F compound	Activity	Laboratory	Year
<i>Ianthella basta</i>	Bastadins	<i>B.i.</i>	Heinrich-Heine Univ, Germany	2006
<i>Ircinia fasciculata</i>	Crude extract	Ab		1994
<i>Ircinia oros</i>	Mixture of Ircinin I & II	Macroalgae	Univ Athens, Greece	2002
<i>Ircinia ramosa</i>	Crude extract	F.bact.	NIO, Goa	2000
<i>Ircinia spinosula</i>	Hydroquinone A	Macroalgae	Univ Athens	2002
	Hydroquinone-C acetate	<i>B.a.</i>	NC Univ, UK	2005
<i>Ircinia variabilis</i>	Crude extract	Macroalgae	Univ Athens	2002
<i>Leiosella idia</i>	Idiadione	<i>S.t.</i> ; <i>H.r.</i>		1985
<i>Mycale adherens</i>	Heteronemin, 12-epi-deoxoscalarin, deacetyl-12,18-diepiscalaradiol, Scalarafuran	<i>H.r.</i>		2005
<i>Pachychalina lunisimilis</i>	Undescribed mixture	<i>S.t.</i> ; <i>H.r.</i>		1985
<i>Petrosia</i> sp.	Crude extract	F.bact.	NIO, Goa	2002
<i>Phyllospongia papyracea</i>	Fatty acid	<i>M.e.</i>	FBP, Japan	1996
<i>Placortis halichondroides</i>	Lactones, phenols, cyclic peroxides	<i>A.l.</i>		1988
<i>Protophlyctaspongia aga</i>	Pyrimidine derivative, Zooanemonin, α -nicotinamide ribose	<i>B.a.</i>	MBI, Japan	2001
<i>Psammaphysilla purpurea</i>	Aplysillamide A, B	Antimicrobial	Japan	1995
	Bromotyrosine alkaloids	F.bact.	NIO, Goa	2004
<i>Pseudoceratina purpurea</i>	Ceratinamine, ceratinamide A, B; Psammaphysin A, Morokaamine, Moloka'iamine 1, 3,5-dibromo-4-methoxy-phenethylamine 2, Pseudoceratidine	<i>B.a.</i>	FBP, Japan	1996
	Bromotyrosine derivative	F.bact. (<i>R.s.</i>)	Japan	2001
	Zammamistatin	Ab	Japan	2001
<i>Reneira sarai</i>	Poly APS	<i>B.a.</i>	CNR, Italy	2003
<i>Spongia officinalis</i>	Crude extract	Ab		1994
<i>Stylotella aurantium</i>	Styloguanidine	<i>B.a.</i>		1995
<i>Toxadocia zumi</i>	Sterol sulphates	<i>S.t.</i>		1985

Z.m., Zebra mussel; *B.n.*, *Bugula neritina*; *B.a.*, *Balanus amphitrite*; *H.e.*, *Hydroides elegans*; *U.c.*, *Ulva conglobata*; *B.i.*, *Balanus improvisus*; Ab, Antibacterial; *H.r.*, *Haliotis rufescens*; *P.pa.*, *Phidolophora pacifica*; *S.t.*, *Salmacina tribranchiata*; Bact., Bacteria; Dtm., Diatom; *N.su.*, *Navicula subinflata*; *N.c.*, *Navicula crucicula*; Af, Antifouling; F.i, Fouling invertebrates; *H.c.*, *Herdmania curvata*; *M.e.*, *Mytilus edulis*; *P.vi.*, *Perna viridis*; *A.l.*, *Agaricia lamarcki*; F.bact., Fouling bacteria; *R.s.*, *Rhodospirillum salexigens*; MBI, Marine Biotechnology Institute; NIO, National Institute of Oceanography; Univ, University; NC Univ, Newcastle University; FBP, Fusetani Biofouling Project; CNR, Consiglio Nazionale delle Ricerche; ARL, Abiko Research Lab; Univ M, University of Massachusetts; Vizag, Vishakapatnam.

antifouling compounds is solvent extraction followed by bioassay-guided fractionation and purification^{40,41}. Thereafter, spectroscopic analysis is carried out for structure elucidation of the isolated compound (Figure 2). The commonly used antifouling assay organisms include fouling bacteria and microalgae, and barnacle cyprids as representatives of the microfouling and macrofouling communities respectively. The antifouling property of the NPA is assessed using 'growth inhibition assay' for fouling bacteria and microalgae and 'settlement inhibition assay' for barnacle cyprids^{23,41-45}. Subsequently, the effective concentration causing 50% inhibition of the test individuals within a specified time period (EC₅₀) and the lethal concentration causing 50% death of the test individuals within a specified time period (LC₅₀) of the NPA are determined. An EC₅₀ of 25 µg/ml or less is the standard set by the US Navy as an efficacy level for NPAs⁴⁶.

From the above observations, the calculated therapeutic ratio (LC₅₀/EC₅₀) of greater than 1 is an essential prerequisite for potential use of the NPA in environmentally compatible antifouling coatings⁴⁷.

Presently, intensive search for NPAs as a natural non-toxic means of fouling control is ongoing in various laboratories worldwide.

Sponges

In spite of having the least differentiated body-plan of all Metazoa, sponges have long been the centre of attention for natural product chemists because they produce a wide array of secondary metabolites, many of unusual chemistry, and often in high concentrations with potent bioactivities⁴⁸⁻⁵⁰. This is further substantiated by the fact that more

Table 2. Antifouling activities detected in soft corals

Softcoral species	A/F compound	Activity	Laboratory	Year
<i>Acanthogorgia turgida</i>	Crude extract	<i>B.a.</i> ; <i>P.vi</i>	RRL, Orissa	1998
<i>Alcyonium paesslerii</i>	Crude extract	Bact.	Univ Mississippi, USA	1995
<i>Cladiella pachyclados</i>	Crude extract	<i>P.vi</i>	NIO, Goa	1998
<i>Cladiella</i> sp.	(-)-6 α -hydroxy polyanthellin	<i>B.a.</i>	NIO, RC, Kochi	Unpl
<i>Dendronephthya</i> sp.	12 α -acetoxy-13,17-seco-cholesta-1,4-dien-3-ones partially purified extract	<i>B.a.</i> <i>M.e.</i>	JRDC, Japan	1999 1993
<i>Dendronephthya</i> sp.	Crude extract	<i>B.a.</i> ; <i>P.vi</i>	RRL, Orissa	1998
<i>Echinogorgia complexa</i>	Crude extract	<i>B.a.</i> ; <i>P.vi</i>	RRL, Orissa	1998
	Crude extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
<i>Echinomuraceae splendens</i>	Caffeine	Dtm.	NIO, Goa	2002
<i>Eunicea</i> sp.	Isothiozalone	Ent.	California, USA	1981
<i>Euplexaura nuttingi</i>	Crude extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
<i>Gersemia antarctica</i>	Crude extract	Bact.	Univ Mississippi, USA	1995
<i>Gorgonella sanguinolenta</i>	Crude extract	<i>B.a.</i> ; <i>P.vi</i>	RRL, Orissa	1998
<i>Juncella juncea</i>	Juncins	<i>B.a.</i>	SCSIO, China	2006
	Partially purified extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
	Juncellins	Bact.	SHMRC, Tuticorin	1993
<i>Leptogorgia virgulata</i>	Homarine	<i>N.sa.</i>	Sk.I.O., Georgia	1983
	Crude extract	<i>B.a.</i>	BML, California	1984
	Partially purified extract	<i>B.n.</i>	Duke Univ. Mar. Lab.,	
	Pukalide; epoxy-pukalide	<i>B.a.</i>	N. Carolina	1988
<i>Lobophytum pauciflorum</i>	Diterpenes	<i>C.f.</i>	J.C. Univ N. Q., Australia	1987
<i>Lobophytum</i> sp.	Diterpenes	B. larvae	RRIMP-NSW, UK	1979
<i>Mauricea fruticosa</i>	Muricins	<i>P.t.</i>	Sc.I.O., USA	1985
<i>Phyllogorgia dilatata</i>	11 β ,12 β -Epoxy-pukalide	<i>P.pe.</i>	U.F.F., Brazil	2006
<i>Pseudopterogorgia Americana</i>	Partially purified extract	<i>N. sp.</i>	Sk.I.O., Georgia	1988
	Furanogermacrene	Dtm.		1989
<i>Pseudopterogorgia acerosa</i>	Partially purified extract	<i>N. sp.</i>	Sk.I.O., Georgia	1988
<i>Renilla reniformis</i>	Partially purified extract	<i>B.n.</i>	Duke Univ. Mar. Lab., N. Carolina	1988
<i>Renilla reniformis</i>	Renillafoulin A	<i>B.a.</i>	Univ of Illinois, USA	1986
<i>Sclerophytum</i> sp.	Crude extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
<i>Sinularia compressa</i>	Crude extract	<i>B.p.</i> ; <i>P.ve</i>	NIO, Goa	2002
<i>Sinularia flexibilis</i>	Sinulariolide; 11-episinulariolide	<i>C.c.</i>	J.C. Univ N. Q., Australia	1997
<i>Sinularia kavarattiensis</i>	Furoic acid	<i>B.a.</i>	NIO, RC, Kochi	Unpl
<i>Sinularia numerosa</i>	Crude extract	<i>P.vi.</i>	NIO, Goa	1998
<i>Sinularia</i> sp.	(-)- β -bisabolene	<i>M.e.</i>	MBI, Japan	1993
	13 α -acetoxy-pukalide and (9E)-4-(6,10-dimethylocta-9-11-dienyl)- furan-2-carboxylic acid	<i>B.a.</i> ; <i>M.e.</i>		1994
<i>Solenocaulon tortuosum</i>	Crude extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
<i>Spongodes</i> sp.	Crude extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
<i>Subergorgia reticulata</i>	Calamenenes	<i>B.a.</i>	NIO, RC, Kochi	Unpl
<i>Subergorgia suberosa</i>	Crude extract	<i>B.a.</i>	SHMRC, Tuticorin	1991
	Crude extract	<i>P.vi.</i>	NIO, Goa	1998
<i>Xenia elongata</i>	Crude extract	Bact.		2002
<i>Xenia macrospiculata</i>	Desoxyhavannahine	Bact.		2005

N.sa., *Navicula salinicola*; *C.f.*, *Ceramium flaccidum*; B. larvae, Barnacle larvae; *P.t.*, *Phaeodactylum tricorutum*; *P.pe.*, *Perna perna*; *N. sp.*, *Navicula*; *B.p.*, *Bacillus pumilus*; *P.ve.*, *Pseudomonas vesicularis*; *C.c.*, *Ceramium codii*; RRL, Regional Research Lab; JRDC, Research Development Corporation of Japan; SHMRC, Sacred Heart Marine Research Centre; SCSIO, South China Sea Institute of Oceanology; Sk.I.O., Skidaway Institute of Oceanography; BML, Biodega Marine Laboratory; J.C. Univ N.Q., James Cook University of North Queensland; RRIMP, Roche Research Institute of Marine Pharmacology; U.F.F., Universidade Federal Fluminense.

than 50% of the NPAs isolated to date are from sponges (Figure 3). Yet sponges remain as one of the most under-explored group of organisms (hardly fewer than 100 species out of more than 10,000 described species have

been investigated) as far as NPAs research is concerned (Table 1).

Sponges are soft-bodied organisms, and as such cannot physically defend themselves from predators and com-

Table 3. Antifouling activity detected in seaweeds

Seaweed species	A/F compound	Activity	Laboratory	Year
<i>Ascophyllum nodosum</i>	Phlorotannins	<i>L.c.</i> ; <i>V.m.</i>	NC Univ, UK	1975
	Fraction	Ab, Af, Dtm., Mcalga, Musl		2004
<i>Bifurcaria bifurcata</i>	Linear diterpenes	B.cyp; F.bact.	France	2004
<i>Bryothamnion seaforthii</i>	Crude extract	<i>P.pe.</i>	CUMS, Brazil	2007
<i>Chondrus crispus</i>	Fraction	Ab, Af, Dtm.,	NC Univ, UK	2004
		Mcalga, Musl		
<i>Costaria costata</i>	Galactosyl and sulpho-quinovosyl- diacylglycerols	<i>M.e.</i>		1990
<i>Delisea pulchra</i>	Furanones	<i>B.a.</i> ; Swd	Australia	1995
<i>Dictyota menstrualis</i>	Dictyol E, Pachydictyol A, Dictyodial	<i>B.n.</i>		1995
<i>Dictyota pfaffii</i>	Diterpene	Af	Brazil	2007
<i>Dilophus okamurai</i>	Spatane diterpene	Abalone larvae		1989
	Diterpene	Antimacfl		1990
<i>Ecklonia radiata</i>	Phlorotannins	<i>U.l.</i>		1997
<i>Ectocarpus siliculosus</i>	Fraction	Ab, Af, Dtm.,	NC Univ., UK	2004
		Mcalga, Musl		
<i>Enteromorpha intestinalis</i>	Fraction	Ab, Af, Dtm., Mcalga, Mussel	NC Univ, UK	2004
<i>Fucus spiralis</i>	Phlorotannins	<i>V.m.</i>		1975
<i>Grateloupia turuturu</i>	Isethionic acid	<i>B.a.</i>	NC Univ, UK	2004
<i>Ishige sinicola</i>	Crude extract	<i>E.p.</i> ; <i>M.e.</i>	PNU, Korea	2001
<i>Jania rubens</i>	Crude extract	<i>P.pe.</i>	CUMS, Brazil	2007
<i>Laurencia obtusa</i>	Elatol	Musl	Brazil	2002
	5 β -Hydroxyaplysiastatin; Palisol; Palisadin A	<i>B.n.</i> ; <i>B.a.</i> ; <i>U. sp.</i>		1998
<i>Laurencia pinnatifida</i>	Crude extract	<i>R.m.</i> ; <i>A. sp.</i>	France	2001
	Fraction	Ab, Af, Dtm., Mcalga, Musl	NC Univ, UK	2004
<i>Laurencia rigida</i>	Elatol, deschloroelatol	<i>B.n.</i> ; <i>B.a.</i>	Brazil	2002
<i>Laurencia sp.</i>	Elatol	<i>B.a.</i>	Australia?	1996
<i>Padina tetrastomatica</i>	Sulpho-quinovosyl diacylglycerols	<i>B.p.</i> , <i>P.ve.</i>	NIO, Goa	2002
	Crude extract			
<i>Plocamium costatum</i>	Halogenated monoterpene	<i>B.a.</i>		1999
<i>Polysiphonia lanosa</i>	Crude extract	<i>E.i.</i> ; <i>U.l.</i>	France	2001
	Fraction	Ab, Af, Dtm., Mcalga, Musl	NC Univ, UK	2004
<i>Ralfsia spongiocarpa</i>	Phlorotannins	Red algae		1975
<i>Rhodomenia paimata</i>	Floridoside	<i>B.a.</i>		2001
<i>Sargassum horneri</i>	Crude extract	<i>E.p.</i>	Dept of Biotech.	2001
<i>Sargassum muticum</i>	Crude extract	<i>R.m.</i> ; <i>A.c.</i> ; <i>E.i.</i> , UI	France	2001
	Fraction	Ab, Af, Dtm., Mcalga, Musl	NC Univ, UK	2004
<i>Sargassum natans</i>	Phlorotannins	Bact., mar. worms		1965
<i>Sargassum vestitum</i>	Phlorotannins	<i>U.l.</i>		1997
<i>Scytosiphon lomentaria</i>	Crude extract	<i>M.e.</i>	Dept of Biotech.	2001
	Phlorotannins	<i>V.m.</i>		1975
<i>Ulva lactuca</i>	Fraction	Ab, Af, Dtm.,	NC Univ, UK	2004
		Mcalga, Musl		
<i>Undaria pinnatifida</i>	Galactosyl and	<i>M.e.</i>		1990

L.c., *Laminaria cloustoni*; *V.m.*, *Vorticella marina*; Mcalga, Macroalga; Musl, Mussel; B.cyp, Barnacle cyprid; Swd, Seaweed; *U.l.*, *Ulva lactuca*; *E.p.*, *Enteromorpha prolifera*; *U. sp.*, *Ulva sp.*; *R.m.*, *Rhodella maculata*; *A.c.*, *Amphora coffeaeformis*; *E.i.*, *Enteromorpha intestinalis*; CUMS, Centro University Monte Serrat; PNU, Pukyong National University.

petitors. To compensate for this, sponges produce an array of chemical metabolites to protect themselves from possible dangers⁵¹. Also, since sponges are voracious filter feeders, they take in along with regular food, the toxic chemicals secreted by other plants and animals, such as corals. They then modify and reuse these chemicals for their defense purposes. Thus, these sponge-produced and

sponge-modified metabolites form the chemical defense mechanism of sponges⁵².

Possible antifouling properties of compounds isolated from sponges was first recognized by Bakus *et al.*⁵³. Since then, a lot of research has been focused in this direction. However, a major breakthrough in the isolation of NPAs from sponges was achieved in the 1990s by the

Table 4. Antifouling activities detected in Ascidians

Ascidian species	Compound	Activity	Laboratory	Year
<i>Amaroucium stellatum</i>	Crude extract	<i>B.a.</i>	UK	2003
<i>Botryllus planus</i>	Crude extract	<i>B.a.</i>	UK	2003
<i>Clavelina lepadiformis</i>	Crude extract	Invert.	UK	1995
<i>Cynthia savignyi</i>	Crude extract	<i>A.s.</i>	Morocco	1999
<i>Distaplia nathensis</i>	Crude extract	Af	India	2003
<i>Eudistoma olivaceum</i>	Eudistomins	<i>B.n.</i>	USA	1990
<i>Eudistoma</i> sp.	Analog of Moroka'iamine	B. larvae		1999
<i>Halocynthia roretzi</i>	Lysophosphatidylinositols	Af; antifungal		1997
<i>Polysyncraton lacazei</i>	Fractions	S.U. larvae	France	1991
<i>Pyura pallida</i>	Crude extract	<i>A.s.</i> ; Microalg	India	1989
<i>Styela pigmentata</i>	Crude extract	<i>A.s.</i> ; Microalg	India	1989

Invert, Invertebrates; *A.s.*, *Artemia salina*; S.U. larvae, Sea Urchin larvae.




Figure 1. Published studies on antifouling research from marine organisms.




Figure 2. Activity chart.

team of researchers of the Fusetani Biofouling Project, Japan under the leadership of Nobuhiro Fusetani. They isolated terpenoids such as kalihinene and 10 β -formamidokalihinol A from the marine sponge *Acanthella cavernosa* and axinyssimide A, B and C from *Axinyssa* sp.; steroid peroxidase from *A. cavernosa*; fatty acid derivative, callytriol C, from *Callyspongia truncata*; bromotyrosine derivatives such as ceratinamide A and psammaphysin from *Pseudoceratina purpurea* and heterocyclic compounds such as pseudoceratidine from *P. purpurea* and mauritiamine from *Agelas mauritiana*. All the above-mentioned compounds were reported to inhibit the settlement of the cosmopolitan biofouler, *Balanus amphitrite*. Of these, 10 β -formamidokalihinol A was the most effective, with an EC_{50} of 0.05 $\mu\text{g/ml}$ and $LC_{50} > 100 \mu\text{g/ml}$ indicating its low toxicity towards barnacle cyprids^{40,54-62}.

Apart from the Fusetani group, search for NPAs from sponges has also been pursued at various other laboratories worldwide. These include Consiglio Nazionale delle Ricerche, Italy; Department of Biology, Slovenia; Department of Pharmacognosy and Chemistry of Natural Products, University of Athens, Greece; Coastal Marine Laboratory, China; Marine Biotechnology Institute, Japan; Duke University Marine Laboratory, North Carolina. The team of researchers at Uppsala University, Sweden has also contributed to sponge antifouling research. According to them, agelasine D from the sponges of the genus *Agelas*, and its two analogues (AV1003A and AKB695), displayed strong inhibitory effect on the settlement of cyprids of *Balanus improvisus*. Agelasine D had an EC_{50} value of 0.11 μM while the two analogues AV1033A and AKB695 had EC_{50} values of 0.23 and 0.3 μM respectively. None of these three compounds caused larval mortality⁵⁰. Recently, antifouling bis-1-oxaquinolizidine alkaloids have been isolated from the sponge, *Haliclona exigua* at the National Institute of Oceanography, India⁴¹. More than 70 NPAs have thus been isolated from marine sponges like *A. cavernosa*, *Agelas mauritiana*, *Aplysina fistularis*, *Axinyssa* sp., *Callyspongia truncata*, *Crambe crambe*, *Crella incrustans*,

Table 5. Antifouling activities detected in miscellaneous groups

Source organism	Compound	Activity	Laboratory	Year
Bryozoans				
<i>Amathia winsoni</i>	Crude extract	Bact.		1993
<i>Orthoscuticella ventricosa</i>	Crude extract	Bact.		1993
<i>Sinupetraliella litoralis</i>		<i>H.c.</i>		2003
<i>Zoobotryon pellucidum</i>	TBG	B. larvae	MBI, Japan	1994
Seagrass				
<i>Zostera marina</i>	Zosteric acid	B. cyprid, Bact., algae, tbwrn	UK	2002
Mangrove species				
<i>Ceriops tagal</i>	Methoxy-ent-8(14)-pimarenyl-15-one ent-8(14)-pimarene-15R,16-diol stigmasterol, β -sitosterol	<i>B.a.</i>	Dept of Biology, China	2008
Bacteria				
<i>Alteromonas</i> sp. (from <i>Halichondria okadai</i>)	Ubiquinone-8	B. larvae		1995
FS-55	Crude extract	F. bact.	HW Univ, UK	2000
<i>NudMB50-11</i>	Crude extract	F. bact.; <i>B.a.</i> ; <i>U.l.</i>		2003
<i>Pseudoalteromonas tunicata</i>		<i>B.a.</i> ; <i>C.i.</i>	Australia	1998
<i>Streptomyces fungicidicus</i>	Diketopiperazines	<i>B.a.</i>	CML, Hong Kong	2006
<i>Vibrio</i> spp. (epiphytic on <i>Dendronephthya</i> sp.)	Polysaccharides	Polych.; Bry.		2003
Cyanobacteria				
<i>Calothrix brevissima</i>	Crude extract	<i>N.p.</i>		1999
<i>Nostoc commune</i>	Comnostins	<i>S.e.</i>		2000
<i>Scytonema hofmanni</i>	Cyanobacterin	<i>N.p.</i>		1999
Fungi				
<i>Cladosporium</i> sp.	Sec. met	<i>B.a.</i>		2006
<i>Ampelomyces</i> sp.	3-Chloro-2,5-dihydroxybenzyl alcohol (CHBA)	Bact.; <i>B.a.</i>		2006
<i>Arthrinium c.f. saccharicola</i>	Sec. met	<i>B.a.</i>		2006
Nudibranchs				
<i>Phyllidia krempfi</i>	Sesquiterpene peroxide	<i>B.a.</i>	FBP, Japan	1996
<i>Phyllidia pustulosa</i>	Sesquiterpenes	<i>B.a.</i>	FBP, Japan	1998
Gastropods				
<i>Trimusculus reticulatus</i>	Labdane diterpene	<i>P.c.</i>		1996
Sea anemones				
<i>Condylactis gigantea</i>	Crude extract	Alg.		1984
Nemertines				
<i>Haplonemertines</i>	Nemertine pyridyl alkaloids	<i>B.a.</i>		2003
Echinoderms				
<i>Astrocyclus caecilian</i>	Crude extract	<i>H.i.</i>	USA	2006
<i>Astropecten articulatus</i>	Crude extract	<i>H.i.</i>	Univ of Alabama	2006
<i>Holothuria leucospilota</i>	Crude extract	<i>N.su.</i> ; <i>N.c.</i>	NIO, Goa	1994
<i>Holothuria scabra</i>	Crude extract	<i>P.vu.</i>	CMFRI, Tvm	2002
<i>Luidia clathrata</i>	Crude extract	<i>H.i.</i>	Birmingham	2006

tbwrn, Tubeworm; *C.i.*, *Ciona intestinalis*; Polych., Polychaete; Bry., Bryozoan; *S.e.*, *Staphylococcus epidermis*; *P.c.*, *Phragmatopoma californica*; Alg., Algae; *H.i.*, *Hincksia irregularis*; *P.vu.*, *Patella vulgata*; HW Univ, Heriot Watt University; CML, Coastal Marine Laboratory; CMFRI, Central Marine Fisheries Research Institute.

Dysidea avara, *Dysidea herbacea*, *Erylus formosus*, *Geodia barretti*, *Haliclona exigua*, *H. koremella*, *Haliclona* sp., *Phyllospongia papyracea*, *Protophlitaspongia* aga, *P. purpurea*, *Reniera sarai* and *Stylotella aurantium* (Table 1).

Soft corals

The investigations on antifouling properties of soft corals gained momentum in the 1980s with many laboratories the world over focusing research in this direction. Scripp's

Institute of Oceanography, Duke University Marine Laboratory and University of Illinois, USA; James Cook University of North Queensland, Australia; Marine Biotechnology Institute, Japan, and South China Sea Institute of Oceanology are some of the major institutions working on the isolation of NPAs from soft corals. Homarine from *Leptogorgia virgulata* and *Leptogorgia setacea*, muricins from *Muricea fruticosa*, renillafooulin from *Renilla reniformis*, pukalide and epoxyukalide from *L. virgulata*, 11-episinulariolide and sinulariolide from *Sinularia flexibilis*, 12 α -acetoxy-13,17-*seco*-cholesta-1,4-dien-3-ones from *Dendronephthya* sp., juncins from *Juncella juncea*, etc. are some of the major NPAs isolated from soft corals^{23–25,63–66}. Scientists at Sacred Heart Marine Research Centre (SHMRC), Tuticorin, in collaboration with Poseidon have isolated an antifouling compound juncellin from the soft coral, *J. juncea*⁶⁷. The NPAs isolated from soft corals are presented in Table 2.

Seaweeds

To date, the halogenated furanone from the red seaweed *Delisea pulchra* isolated by Stefan Kjelleberg and Peter Steinberg of the Centre for Marine Biofouling and Bioinnovation, Australia, has proved the most successful, with EC₅₀ being as low as 0.02 μ g/ml and their activities comparable to, or even better than, those obtained with commercial biocides²⁹. Also, dictyols from *Dictyota menstrualis* and sesquiterpenes from *Laurencia rigida* inhibit the settlement of macrofoulers such as *Bugula neritina* and *Bugula amphitrite*^{68,69}. The antifouling activity detected in seaweeds is listed in Table 3.

Ascidians

The NPAs isolated from ascidians are listed in Table 4, the major ones being eudistomins and lysophosphatidyl inositols from *Eudistoma olivaceum* and *Halocynthia roretzi* respectively⁷⁰.




Figure 3. NPAs isolated from marine sources.

Miscellaneous

Bryozoans, nemerteans, molluscs, echinoderms, seagrasses, mangroves, microorganisms, etc. have also been explored for the presence of NPAs. The major findings are presented in Table 5.

Bryozoans: Tribromogramine (TBG) isolated from the bryozoan *Zoobotryon pellucidum* by Wataru Miki at the Marine Biotechnology Institute in Tokyo is a promising NPA. TBG is only one-tenth as toxic as TBT, but is 6–8 times as potent when it comes to the inhibition of larval settlement³³.

Nemerteans: The nemertine pyridyl alkaloids from the marine Haplonemertines have potent antifouling activity against the larvae of the barnacle *B. amphitrite*⁷¹.

Molluscs: The marine molluscs, *Nerita albicilla* and *N. oryzae* from Tuticorin showed broad spectral inhibitory activity against biofilm bacteria⁷². The extract of molluscan egg case also exhibited antifouling activity against fouling bacteria³⁹.

Echinoderms: The crude extracts of holothurians have been reported to exhibit antifouling properties. For example, the methanol extract of *Holothuria leucospilota* inhibited the fouling diatoms, *Navicula subinflata* and *N. crucicula*³⁷. Crude extract of *H. scabra* also showed antifouling activity against the limpet, *Patella vulgata*⁷³.

Seagrasses: Zosteric acid from the seagrass, *Zostera marina* was found to inhibit micro- and macro-fouling organisms⁷⁴.

Mangroves: There is scant information on isolation of antifouling compounds from mangrove species. One new diterpene, methoxy-ent-8(14)-pimarenyl-15-one, and three known metabolites, ent-8(14)-pimarene-15R,16-diol, stigmasterol and β -sitosterol were isolated from the roots of *Ceriops tagal*. These compounds showed potent non-toxic antifouling activities against larval settlements of *B. albicostatus*³⁶.

Microorganisms: The advantage of using microorganisms as the source for NPAs is that the compounds can be produced fairly rapidly and in large quantities in bioreactors unlike the invertebrates like sponges, soft corals, etc. wherein large quantities of organisms would have to be collected to gain a small quantity of the compound.

Among bacteria, *Pseudoalteromonas tunicata*, isolated from the surface of a tunicate, showed antifouling activity against *B. amphitrite* and *Ciona intestinalis* larvae^{75,76}. They produced at least five compounds that inhibited the settlement or development of a range of surface colonizing species^{76,77} while ubiquinone from *Alteromonas* sp.

(isolated from surface of *Halichondria okadai*) inhibited settlement of barnacles³⁵. Also, antifouling diketopiperazines have been isolated from a deep-sea bacterium, *Streptomyces fungicidicus*⁷⁸.

Bacteria growing on the surfaces of larvae of some crustaceans produce antimicrobial compounds which protect the developing larvae from infections^{39,79,80}. Bacteria isolated from the seaweeds have also been shown to release compounds that repel other fouling bacteria, suggesting that they may protect the seaweed from fouling by other organisms⁸¹.

Fungi and cyanobacteria have also yielded NPAs. 3-chloro-2,5-dihydroxybenzyl alcohol (CHBA) from the fungus *Ampelomyces* sp. was detected to have antibacterial and larval settlement inhibition (*B. amphitrite*) properties and cyanobacteria from the cyanobacterium *Scytonema hofmanni* was effective against the fouling benthic diatom *Nitzschia pusilla*^{46,82}.

NPAs having potential for commercialization

Although numerous NPAs with antisetlement activities have been reported to date, only in a few, but growing number of cases, compounds with potential as replacements for toxic, metal-based antifoulants have been discovered⁸³ (Figure 4). Some of these NPAs have higher activities compared with those of organotin compounds and copper compounds¹⁵.

Among sponges, polymeric 3-alkylpyridinium salts (poly-APS) isolated from *Reniera sarai* at Consiglio Nazionale delle Ricerche, Italy and Department of Biology, Slovenia, exhibited an EC₅₀ of 0.27 µg/ml and LC₅₀ of 30 µg/ml against *B. amphitrite* cyprids⁶¹. On account of its low toxicity, solubility, stability, reversibility and ease in synthesis, poly-APS is portrayed as a promising nontoxic NPA. Poly-APS inhibits acetylcholine esterase enzyme in barnacle cyprids which has a neurotransmitter/neuromodulator role in settlement of barnacle cyprids⁶¹. 10 β-formamidokalihinol A, a terpenoid with a chlorine group attached to its structure, is another potential NPA with EC₅₀ of 0.05 µg/ml and LC₅₀ > 100 µg/ml indicating its low toxicity towards barnacle cyprids⁴⁰. The NPA agelasine D from the sponges of the genus *Agelas*, together with its two analogues, i.e. AV1003A and AKB695, displayed a strong inhibitory effect on settlement of *B. improvisus* cyprid larvae. Agelasine D had an EC₅₀ value of 0.11 µM while the two analogues AV1033A and AKB695 had EC₅₀ values of 0.23 and 0.3 µM respectively. None of these three compounds affected larval mortality indicating its potential as an environmentally-compatible NPA⁵⁰. The sesquiterpene hydroquinone, avarol, isolated from *Dysidea avara* at the Department of Pharmacognosy and Chemistry of Natural Products, University of Athens, Greece, has good future prospects on account of the significant anti-settlement activity exhi-

bited by its analogue, 4'-propylthioavarone against cyprids of the barnacle, *B. amphitrite*. It also exhibited a therapeutic ratio of more than 40, highlighting its non-toxic nature⁶².

Among soft corals, *Leptogorgia virgulata* and *Renilla reniformis* have been studied intensively for isolating NPAs^{23–25,84,85} resulting in the isolation of pukalide with an EC₅₀ of 0.05 µg/ml and renillafoulin A with an EC₅₀ of 0.02–0.2 µg/ml against *B. amphitrite*. These NPAs also produced encouraging results in the field as well. However, renillafoulin and pukalide are comparatively complex and thus are not amenable for commercial exploitation. Therefore, analogues of pukalide and renillafoulin were synthesized and evaluated for antifouling activity. Among the analogues, khellin exhibited promising antifouling activity and was effective in preliminary field trials⁸⁶.




Figure 4. Structures of potential NPAs from marine organisms.

Although there are not many potential NPAs from seaweeds, the most promising NPA, furanone, is from the red seaweed, *Delisea pulchra*. Furanones act by inhibition of the microfouling bacteria. But it remains to be tested whether this automatically prevents barnacle attachment, and if not, how the furanones act against the barnacles.

The most successful NPA isolated from ascidians so far is eudistomins from *Eudistoma olivaceum*. They were found to inhibit larval settlement of *B. neritina* at concentrations⁷⁰ less than 2.2 µg/cm².

Also, 2,5,6-tribromo-1-methyl gramine from *Zoobotryon pellucidum*, having remarkable antifouling activity, is projected as potential non-toxic antifoulant with possible scope for commercialization. Its analogue 5,6-dichlorogramine exhibited potent activity against barnacle larvae and mussels (EC₅₀ 4 ng/ml)^{33,87}. 2,5,6-tribromo-1-methyl gramine is believed to inhibit serotonergic neurons in barnacle cyprids, which is essential for settlement⁸⁸.

Similarly, 3-chloro-2,5-dihydroxybenzyl alcohol isolated from the fungus *Ampelomyces* sp. is also having bright commercial prospects on account of its low toxicity (therapeutic ratio >80) and simple molecular structure⁴⁶.

NPA-based paints

Intensive research towards the development of NPA-based paints is progressing worldwide and results seem to be highly encouraging. However, much of these information are trade secrets and hence, not much details are available in a documented form. In general, the available information suggests that NPA-based paints are formulated mainly by using analogues, as the organisms produce NPAs only in trace amounts.

Some of the NPA-based antifouling paints such as 'Sea Nine-211', 'Netsafe' and 'Pearlsafe' have already been commercialized. The NPA in 'Sea Nine-211' paint is 4,5-dichloro-2-*n*-octyl-4-isothiazolin-3-one (DCOI), a member of the isothiazolone family. Similarly, 'Netsafe' and 'Pearlsafe' are developed from analogues of furanone isolated from Australian red seaweed, *D. pulchra*²⁹.

Another antifouling paint being developed consists of 5,6-dichlorogramine, an analogue of 2,5,6-tribromo-1-methylgramine isolated from *Z. pellucidum*. It was coated on the surface of acryl board, and the board was found to be fouling-free even after two months in seawater¹⁵.

Also, reports are available on extracts being directly used in antifouling coatings. For example, extracts of the sea pansy, *R. reniformis*, added to commercially available paint and encapsulated in metallic microtubules^{86,89,90} were effective in controlling biofouling over short periods in the marine environment. Paint formulations incorporating extracts of sponges were also active in barnacle settling assays⁹¹. Apart from this, one paint containing

extract of epiphytic bacteria, *Pseudomonas* sp. strain, NUDMB50-11, showed excellent antifouling activity⁷⁶.

Major issues in NPAs research

A major issue for NPAs is finding an environmentally responsible way of obtaining adequate supplies of the compounds of interest. Possible ways to overcome this problem include aquaculture, cell culture, analogue development, chemical synthesis, and particularly with regard to bacteria, genetic manipulation and fermentation technology^{83,92}. For comparatively simple molecules, chemical synthesis may be the favoured option.

Similarly, the controlled leaching of the natural compounds at desired concentrations after incorporation in antifouling coatings for long-term duration is another challenge confronting the NPAs scientists. Mimicking natural release concentrations by the parent organisms at environmentally safe concentrations may be a tedious task ahead. Method for controlling the release of natural products was investigated by Price *et al.*⁸⁹ using microencapsulation technologies. However, more intensive collaborative research efforts involving biologists, organic chemists, polymer and paint technologists are necessary for achieving this goal.

The most widely held view is that the preferred future antifouling system includes a bioactive ingredient, with less non-target toxic effects, and incorporated in a marine paint to deter colonization rather than killing of established foulers.

Conclusion

This review highlights the potential of NPAs as alternatives to TBT-based antifouling coatings. Over 145 NPAs have so far been isolated from various marine organisms. Among these, more than 10 are labelled as potential NPAs owing to their high activity with relatively low toxicity. One of the major problems hampering the development of many promising NPAs is ensuring supply commensurate with the needs of the antifouling paint industry. Unfortunately, NPAs are produced in trace amounts and therefore, relying on source organism may not be a feasible option. Chemical synthesis is the direct way for assuring adequate supply, but most likely, it will be an expensive affair. Another alternative is to develop analogues of NPAs with simple structures that can be synthesized in a cost-effective manner. Of late, more research is focused on the isolation of NPAs from microorganisms, considering the possibility of large scale production, because these organisms are easy to harvest within the laboratory. In spite of all these impediments, the successful commercialization of a few NPA-based antifouling coatings such as Sea Nine-211, Netsafe and Pearlsafe provides optimism.

For every natural cause there is a natural solution. Let us have patience to identify and implement it to protect and preserve Mother Nature for the future generations.

1. WHOI, Woods Hole Oceanographic Institution, *Marine fouling and its prevention*, US Naval Institute Press, Annapolis, MD, 1952.
2. Costlow, J. D. and Tipper, R. C., *Marine Biodeterioration: an Interdisciplinary Study*, US Naval Institute, Annapolis, 1984.
3. Abarzua, S. and Jacobowsky, S., Biotechnological investigations for the prevention of biofouling. 1. Biological and biochemical principles for the prevention of biofouling. *Mar. Ecol. Prog. Ser.*, 1995, **123**, 301–312.
4. Olsen, S. M., Pedersen, L. T., Laursen, M. H., Kiil, S. and Dam-Johansen, K., Enzyme-based antifouling coatings: a review. *Biofouling*, 2007, **23**, 369–383.
5. Bhadury, P. and Wright, P. C., Exploitation of marine algae: biogenic compounds for potential antifouling applications. *Planta*, 2004, **219**, 561–578.
6. Chambers, L. D., Stokes, K. R., Walsh, F. C. and Wood, R. J. K., Modern approaches to marine antifouling coatings. *Surface Coatings Technol.*, 2006, **201**, 3642–3652.
7. Kiil, S., Dam-Johansen, K., Weinell, C. E. and Pedersen, M. S., Seawater-soluble pigments and their potential use in self-polishing antifouling paints: simulation based screening tool. *Prog. Org. Coat.*, 2002, **45**, 423–434.
8. Pidgeon, J. D., *Critical Review of Current and Future Marine Antifouling Coatings*, Report No. 93/TIPEE/4787. Lloyd's Register Engineering Services, 1993.
9. Watermann, B., *Alternative Antifouling Techniques: Present and Future?* Report, LimnoMar, Hamburg, Germany, 1999, p. 6.
10. His, E. and Robert, R., Comparative effects of two antifouling paints on the oyster *Crassostrea gigas*. *Mar. Biol.*, 1987, **95**, 83–86.
11. Alzieu, C., Environmental problems caused by TBT in France: assessment, regulations, prospects. *Mar. Environ. Res.*, 1991, **32**, 7–17.
12. Gibbs, P. E., Bryan, G. W., Pascoe, P. L. and Burt, G. R., The use of the dogwhelk, *Nucella lapillus*, as an indicator of tributyl tin (TBT) contamination. *J. Mar. Biol. Ass. UK*, 1987, **67**, 507–523.
13. Bailey, S. K. and Davies, I. M., Continuing impact of TBT, previously used in mariculture, on Dogwhelk (*Nucella lapillus* L.) populations in a Scottish Sea Loch. *Mar. Environ. Res.*, 1991, **32**, 186–199.
14. Champ, M. A., A review of organotin regulatory strategies, pending actions, related costs and benefits. *Sci. Total Environ.*, 2000, **258**, 21–71.
15. Omae, I., General aspects of tin-free antifouling paints. *Chem. Rev.*, 2003, **103**, 3431–3448.
16. Kime, D. E., The effects of pollution on reproduction in fish. *Rev. Fish Biol. Fish.*, 1995, **5**, 52–96.
17. Clare, A. S., Rittschof, D., Gerhart, D. J. and Maki, J. S., Molecular approaches to non-toxic antifouling. *Invert. Reprod. Dev.*, 1992, **22**, 67–76.
18. Fusetani, N., Biofouling and antifouling. *Nat. Prod. Rep.*, 2004, **21**, 94–104.
19. Turk Robert, T. F. and Sepcic, K., Mechanisms of toxicity of 3-alkylpyridinium polymers from marine sponge *Reniera sarai*. *Mar. Drugs*, 2007, **5**, 157–167.
20. Thompson, J. E., Walker, R. P. and Faulkner, D. J., Screening and bioassays for biologically-active substances from forty marine sponge species from San Diego, California, USA. *Mar. Biol.*, 1985, **88**, 11–21.
21. Goto, R., Kado, R., Muramoto, K. and Kamiya, H., Fatty acids as antifoulants in a marine sponge. *Biofouling*, 1992, **6**, 61–68.
22. Van Altena, I. and Butler, A. J., In *Biofouling: Problems and Solutions* (eds Kjelleberg, S. and Steinberg, P.), The University of New South Wales, Sydney, 1994, pp. 80–86.
23. Targett, N. M., Bishop, S. S., McConell, O. J. and Yoder, J. A., Antifouling agents against the benthic marine diatom, *Navicula salinicola*: homarine from the gorgonians *Leptogorgia virgulata* and *L. setacea* and analogs. *J. Chem. Ecol.*, 1983, **9**, 817–829.
24. Keifer, P. A., Rinehart Jr, K. L. and Hooper, I. R., Renilla-fouling, antifouling diterpenes from the sea pansy *Renilla reniformis* (Octocorallia). *J. Org. Chem.*, 1986, **51**, 4450–4454.
25. Gerhart, D. J., Rittschof, D. and Mayo, S. W., Chemical ecology and the search for marine antifoulants. Studies of a predator-prey symbiosis. *J. Chem. Ecol.*, 1988, **14**, 1905–1917.
26. Rittschof, D., Natural product antifoulants: one perspective on the challenges related to coatings development. *Biofouling*, 2000, **15**, 119–127.
27. Sieburth, J. M. and Conover, J. T., *Sargassum* tannin, an antibiotic which retards fouling. *Nature*, 1965, **208**, 52–53.
28. Zapata, O. and McMillan, C., Phenolic acids in seagrasses. *Aquat. Bot.*, 1979, **7**, 307–317.
29. De Nys, R., Steinberg, P. D., Willemsen, R., Dworjany, S. A., Gabelish, C. L. and King, R. J., Broad-spectrum effects of secondary metabolites from the red alga *Delisea pulchra* in antifouling assays. *Biofouling*, 1995, **8**, 259–271.
30. Davis, A. R., Alkaloids and ascidian defense: evidence for the ecological role of natural products from *Eudistoma olivaceum*. *Mar. Biol.*, 1991, **111**, 375–379.
31. Tsukamoto, S., Hirota, H., Kato, H. and Fusetani, N., Urochordamines A and B: larval settlement/metamorphosis-promoting, pteridine-containing physostigmine alkaloids from the tunicate *Ciona savignyi*. *Tetrahedron Lett.*, 1993, **34**, 4819–4822.
32. Walls, J. T., Ritz, D. A. and Blackman, A. J., Fouling, surface bacteria and antibacterial agents of four bryozoan species found in Tasmania. *J. Exp. Mar. Biol. Ecol.*, 1993, **169**, 1–13.
33. Kon-ya, K., Shimizu, N., Adachi, K. and Miki, W., 2,5,6-tribromo-1-methylgramine, an antifouling substance from the marine bryozoan *Zoobotryon pellucidum*. *Fish. Sci.*, 1994, **60**, 773–775.
34. Kjelleberg, S. and Holmstrom, C., Antifoulants from bacteria. In *Biofouling: Problems and Solutions*. Proceedings of the International Workshop (eds Kjelleberg, S. and Steinberg, P.), The University of New South Wales, Sydney, 1994, pp. 65–69.
35. Kon-ya, K., Shimizu, N., Otaki, N., Yokoyama, A., Adachi, K. and Miki, W., Inhibitory effect of bacterial ubiquinones on the settling of barnacle, *Balanus amphitrite*. *Experientia*, 1995, **51**, 153–155.
36. Chen, J. D., Feng, D. Q., Yang, Z. W., Wang, Z. C., Qiu, Y. and Lin, Y. M., Antifouling metabolites from the mangrove plant *Ceriops tagal*. *Molecules*, 2008, **13**, 212–219.
37. Mokashe, S. S., Garg, A., Anil, A. C. and Wagh, A. B., Growth inhibition of periphytic diatoms by methanol extracts of sponges and holothurians. *Indian J. Mar. Sci.*, 1994, **23**, 57–58.
38. Greer, S. P., Iken, K., McClintock, J. B. and Amsler, C. D., Bioassay-guided fractionation of antifouling compounds using computer-assisted motion analysis of brown algal spore swimming. *Biofouling*, 2006, **22**, 125–132.
39. Ramasamy, M. S. and Murugan, A., Fouling deterrent chemical defence in three muricid gastropod egg masses from the Southeast coast of India. *Biofouling*, 2007, **23**, 259–265.
40. Yang, L. H., Lee, O. O., Jin, T., Li, X. C. and Qian, P. Y., Antifouling properties of 10 β -formamidokalihinol and kalihinol A isolated from the marine sponge *Acanthella cavernosa*. *Biofouling*, 2006, **22**, 1–10.
41. Limna Mol, V. P., Raveendran, T. V. and Parameswaran, P. S., Antifouling activity exhibited by secondary metabolites of the marine sponge, *Haliclona exigua* (Kirkpatrick). *Int. Biodeter. Biodegr.*, 2009, **63**, 67–72.

42. Wilsanand, V., Wagh, A. B. and Bapuji, M., Antifouling activities of octocorals on some marine microfoulers. *Microbios*, 2001, **104**, 131–140.
43. Hellio, C., Maréchal, J.-P., Ve'ron, B., Bremer, G., Clare, A. S. and Gal, Y. L., Seasonal variation of antifouling activities of marine algae from Brittany coast (France). *Mar. Biotechnol.*, 2004, **6**, 67–82.
44. Qi, S. H., Zhang, S., Yang, L. H. and Qian, P. Y., Antifouling and antibacterial compounds from the gorgonians *Subergorgia suberosa* and *Scripearia gracillis*. *Nat. Prod. Res.*, 2008, **22**, 154–166.
45. Briand, J.-F., Marine antifouling laboratory bioassays: an overview of their diversity. *Biofouling*, 2009, **25**, 297–311.
46. Kwong, T. F. N., Miao, L., Li, X. and Qian, P. Y., Novel antifouling and antimicrobial compound from a marine-derived fungus *Ampelomyces* sp. *Mar. Biotechnol.*, 2006, **8**, 634–640.
47. Rittschof, D., Lai, C. H., Kok, L. M. and Teo, S. L. M., Pharmaceuticals as antifoulants: concept and principles. *Biofouling*, 2003, **19**, 207–212.
48. McCaffrey, E. J. and Edean, R., Antimicrobial activity of tropical and subtropical sponges. *Mar. Biol.*, 1985, **89**, 1–8.
49. Bobzin, S. C. and Faulkner, D. J., Chemistry and chemical ecology of the Bahamian sponge *Aplysilla glacialis*. *J. Chem. Ecol.*, 1992, **18**, 309–332.
50. Sjogren, M., Dahlstrom, M., Hedner, E., Jonsson, P. R., Vik, A., Gundersen, L. L. and Bohlin, L., Antifouling activity of brominated cyclopeptides from the marine sponge *Geodia barretti*. *Biofouling*, 2008, **24**, 251–258.
51. Thakur, N. L. and Muller, W. E. G., Biotechnological potential of marine sponges. *Curr. Sci.*, 2004, **86**, 1506–1512.
52. Hooper, J. N. A., 'Spongicide'. Guide to sponge collection and identification. Queensland Museum, Australia, 2000.
53. Bakus, G. J., Evans, T., Mading, B. and Kourou, P., The use of natural and synthetic toxins as shark repellents and antifouling agents. *Toxicol.*, 1983, **3**, 25–27.
54. Okino, T., Yoshimura, E., Hirota, H. and Fusetani, N., Antifouling kalihinenes from the marine sponge *Acanthella cavernosa*. *Tetrahedron Lett.*, 1995, **36**, 8637–8640.
55. Hirota, H., Tomono, Y. and Fusetani, N., Terpenoids with antifouling activity against barnacle larvae from the marine sponge *Acanthella cavernosa*. *Tetrahedron*, 1996, **52**, 2359–2368.
56. Kato, T., Shizuri, Y., Izumida, H., Yokoyama, A. and Endo, M., Styloguanidines, new chitinase inhibitors from the marine sponge *Stylorella aurantium*. *Tetrahedron Lett.*, 1995, **36**, 2133–2136.
57. Tsukamoto, S., Kato, H., Hirota, H. and Fusetani, N., Pseudoceratidine: a new antifouling spermidine derivative from the marine sponge *Pseudoceratina purpurea*. *Tetrahedron Lett.*, 1996, **37**, 1439–1440.
58. Tsukamoto, S., Kato, H., Hirota, H. and Fusetani, N., Antifouling terpenes and steroids against barnacle larvae from marine sponge. *Biofouling*, 1997, **11**, 283–291.
59. Hirota, H., Okino, T., Yoshimura, E. and Fusetani, N., Five new antifouling sesquiterpenes from two marine sponges of the genus *Axinyssa* and the nudibranch *Phyllidia pustulosa*. *Tetrahedron*, 1998, **54**, 13971–13980.
60. Hattori, T., Matsuo, S., Adachi, K. and Shizuri, Y., Isolation of antifouling substances from the Palauan sponge *Protosphittaspongia aga*. *Fisheries Sci.*, 2001, **67**, 690–693.
61. Faimali, M., Sepčić, K., Turk, T. and Geraci, S., Non-toxic antifouling activity of polymeric 3-alkylpyridinium salts from the Mediterranean sponge *Reniera sarai* (Pulitzer-Finali). *Biofouling*, 2003, **19**, 47–56.
62. Tsoukatou, M. et al., Evaluation of the activity of the sponge metabolites avarol and avarone and their synthetic derivatives against fouling micro- and macro-organisms. *Molecules*, 2007, **12**, 1022–1034.
63. Bandurraga, M. M. and Fenical, W., Isolation of the muricins. Evidence of a chemical adaptation against fouling in the marine octocoral *Muricea fruticosa* (Gorgonacea). *Tetrahedron*, 1985, **41**, 1057.
64. Michalek, K. and Bowden, B. F., A natural algicide from soft coral *Sinularia flexibilis* (Coelenterata, Octocorallia, Alcyonacea). *J. Chem. Ecol.*, 1997, **23**, 259–273.
65. Tomono, Y., Hirota, H. and Fusetani, N., Isogosterones A–D, antifouling 13,17-secosteroids from an octocoral *Dendronephthya* sp. *J. Org. Chem.*, 1999, **64**, 2272–2275.
66. Qi, S. H., Zhang, S., Qian, P. Y., Xiao, Z. H. and Li, M. Y., Ten new antifouling briarane diterpenoids from the South China Sea gorgonian *Juncella juncea*. *Tetrahedron*, 2006, **62**, 9123–9130.
67. Avelin, Mary Sr., Vitalina, Mary Sr., Rittschof, D. and Nagabhushanam, R., Bacterial–barnacle interaction: potential of using juncellins and antibiotics to alter the structure of bacterial communities. *J. Chem. Ecol.*, 1993, **19**, 2155–2167.
68. Schmitt, T. M., Lindquist, N. and Hay, M. E., Seaweed secondary metabolites as antifoulants: effects of *Dictyota* spp. diterpenes on survivorship, settlement, and development of marine invertebrate larvae. *Chemoecology*, 1998, **8**, 125.
69. de Nys, R., Leya, T., Maximilien, R., Asfar, A., Nair, P. S. R. and Steinberg, P. D., The need for standardised broad scale bioassay testing: a case study using the red alga *Laurencia rigida*. *Biofouling*, 1996, **10**, 213–224.
70. Davis, A. R. and Wright, A. E., Inhibition of larval settlement by natural products from the ascidian, *Eudistoma olivaceum* (van Name). *J. Chem. Ecol.*, 1990, **16**, 1349–1357.
71. Kem, W. R., Soti, F. and Rittschof, D., Inhibition of barnacle larval settlement and crustacean toxicity of some haplonemertine pyridyl alkaloids. *Biomol. Eng.*, 2003, **20**, 355–361.
72. Ramasamy, M. S. and Murugan, A., Potential antimicrobial activity of marine molluscs from Tuticorin, Southeast Coast of India Against 40 biofilm bacteria. *J. Shellfish Res.*, 2005, **24**, 243–251.
73. Lipton, A. P. and Selvin, J., Development of a rapid 'mollusc foot adherence bioassay' for detecting potent antifouling bioactive compounds. *Curr. Sci.*, 2002, **83**, 735–737.
74. Harrison, P. G. and Chan, A. T., Inhibition of the growth of microalgae by extracts of eelgrass (*Zostera marina*) leaves. *Mar. Biol.*, 1980, **61**, 21–26.
75. James, S. G., Holmstrom, C. and Kjelleberg, S., Purification and characterisation of a novel antibacterial protein from the marine bacterium D2. *Appl. Environ. Microbiol.*, 1996, **62**, 2783–2788.
76. Holmstrom, C. and Kjelleberg, S., Marine Pseudoalteromonas species are associated with higher organisms and produce biologically active extracellular agents. *FEMS Microbiol. Ecol.*, 1999, **30**, 285–293.
77. Burgess, J. G., Boyd, K. G., Armstrong, E., Jiang, Z., Yan, L., Berggren, M., May, U., Pisacane, T., Granmo, A. and Adams, D. R., The development of a marine natural product-based antifouling paint. *Biofouling*, 2003, **19**, 197–205.
78. Li, X., Dobretsov, S., Xu, Y., Xiao, X., Hung, O. S. and Qian, P. Y., Antifouling diketopiperazines produced by a deep-sea bacterium, *Streptomyces fungicidicus*. *Biofouling*, 2006, **22**, 201–208.
79. Gil-Tumes, M. S., Hay, M. E. and Fenical, W., Symbiotic marine bacteria chemically defend crustacean embryos from a pathogenic fungus. *Science*, 1989, **246**, 116–118.
80. Gil-Tumes, M. S. and Fenical, W., Embryos of *Homarus americanus* are protected by epibiotic bacteria. *Biol. Bull.*, 1992, **182**, 105–108.
81. Burgess, J. G., Jordan, E. M., Bregu, M., Mearns-Spragg, A. and Boyd, K. G., Microbial antagonism: a neglected avenue of natural products research. *J. Biotechnol.*, 1999, **70**, 27–32.
82. Abarzua, S., Jakubowski, S., Eckert, S. and Fuchs, P., Biotechnological investigation for the prevention of marine biofouling II. Blue-green algae as potential producers of biogenic agents for the growth inhibition of microfouling organisms. *Bot. Mar.*, 1999, **42**, 459–465.

83. Clare, A. S., Rittschof, D., Gerhart, D. J., Hooper, I. R. and Bonaventura, J., Antisettlement and narcotic action of analogues of diterpene marine natural product antifoulants from octocorals. *Mar. Biotechnol.*, 1999, **1**, 427–436.
84. Standing, D. J., Hooper, I. R. and Costlow, J. D., Inhibition and induction of barnacle settlement by natural products present in octocorals. *J. Chem. Ecol.*, 1984, **10**, 823–834.
85. Rittschof, D., Hooper, I. R., Branscomb, E. S. and Costlow, J. D., Inhibition of barnacle settlement and behavior by natural products from whip corals, *Leptogorgia virgulata* (Lamarck, 1815). *J. Chem. Ecol.*, 1985, **11**, 551–563.
86. Clare, A. S., Thomas, R. F. and Rittschof, D., Evidence for the involvement of cyclic AMP in the pheromonal modulation of barnacle settlement. *J. Exp. Biol.*, 1995, **198**, 655–664.
87. Kon-ya, K., Shimizu, N., Miki, W. and Endo, M., Indole derivatives as potent inhibitors of larval settlement by the barnacle, *Balanus amphitrite*. *Biosci. Biotechnol. Biochem.*, 1994, **58**, 2178–2181.
88. Yamamoto, H., Tachibana, A., Kawaii, S., Matsumura, K. and Fusetani, N., Serotonin involvement in larval settlement of the barnacle, *Balanus amphitrite*. *J. Exp. Zool. Part A: Compar. Exp. Biol.*, 1998, **275**, 339–345.
89. Price, R. P., Patchan, M., Clare, A. S., Rittschof, D. and Bonaventura, J., Performance enhancement of natural antifouling compounds and their analogs through microencapsulation and controlled release. *Biofouling*, 1992, **6**, 207–216.
90. Price, R. P., Patchan, M., Clare, A. S., Rittschof, D. and Bonaventura, J., Performance enhancement of natural antifouling compounds and their analogs through microencapsulation and controlled release. In *Recent Developments in Biofouling Control* (eds Thompson, M. F. *et al.*), A. A. Balkema, Rotterdam, 1994, pp. 321–334.
91. Willemsen, P. R. and Ferrari, G. M., The use of antifouling compounds from sponges in antifouling paints. *Surf. Coat. Int.*, 1993, **10**, 423–427.
92. Clare, A. S., Towards nontoxic antifouling. *J. Mar. Biotechnol.*, 1998, **6**, 3–6.

ACKNOWLEDGEMENTS. This work was funded by CMLRE, MoES. We thank the Director, NIO and the Scientist-in-Charge, NIO, RC, Kochi for their encouragement and support. We are grateful to Dr V. P. Venugopalan, IGCAR, Kalpakkam for his relevant and constructive comments which have greatly helped in improving this manuscript. V. P. Limna Mol gratefully acknowledges CSIR, New Delhi for the grant of Senior Research Fellowship. This work is NIO contribution no. 4568.

Received 5 January 2009; revised accepted 24 June 2009
